

Thermal Performance Data

Visions 3500 Double Hung Windows (9108)

(non J-channel)




ENERGY PERFORMANCE DATA								US ENERGY STAR V 6.0		CANADIAN ENERGY PERFORMANCE DATA				CANADA ENERGY STAR v 4.1				
NFRC Total Unit Calculations ^a								US ENERGY STAR V 6.0		CANADIAN ENERGY PERFORMANCE DATA				CANADA ENERGY STAR v 4.1				
Grille Option	Glazing thickness	Glazing Option ^b	CPD #	U Value	Solar Heat Gain Coefficient	Visible Light Transmittance	Condensation Resistance Rating	US ENERGY STAR V 6.0				U-Value (metric)	Maximum Air Leakage L/s/m ²	Air Infiltration/Exfiltration Average	Energy Rating	CANADA ENERGY STAR v 4.1		
								N	NC	SC	S					1	2	3
No GIA or SDL	3/4"	Clear Insul	WEA-N-289-00040-00001	0.45	0.59	0.62	45					2.56	0.6	1.32	15			
	3/4"	Insul Low-E	WEA-N-289-00046-00001	0.31	0.32	0.54	56					1.76	0.6	1.32	17			
	3/4"	Insul Low E w/Argon	WEA-N-289-00052-00001	0.27	0.32	0.54	62	Y	Y			1.53	0.6	1.32	22	Y		
	3/4"	Bronze Low E	WEA-N-289-00048-00011	0.31	0.30	0.40	56					1.76	0.6	1.32	16			
	3/4"	Bronze Low E w/Argon	WEA-N-289-00055-00011	0.28	0.30	0.40	60		Y			1.59	0.6	1.32	20	Y		
	3/4"	Insul Low-E 340	WEA-N-289-00105-00001	0.31	0.14	0.29	57				Y	1.76	0.6	1.30	7			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-289-00120-00001	0.28	0.14	0.29	60		Y	Y	Y	1.59	0.6	1.30	11			
	3/4"	Zo-e-shield 5	WEA-N-289-00061-00001	0.31	0.21	0.49	57				Y	1.76	0.6	0.01	14			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-289-00079-00001	0.27	0.21	0.49	61	Y	Y	Y	Y	1.53	0.6	1.30	16	Y		
	3/4"	Zo-e-shield 5 Extreme	WEA-N-289-00065-00001	0.26	0.21	0.48	44	Y	Y	Y	Y	1.48	0.6	1.32	17	Y		
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-289-00083-00001	0.24	0.20	0.48	48	Y	Y	Y	Y	1.36	0.6	1.30	19	Y		
	3/4"	Insul Low-E 180	WEA-N-289-00095-00001	0.32	0.52	0.60	56					1.82	0.6	1.30	28	Y		
	3/4"	Insul Low E 180 w/Argon	WEA-N-289-00110-00001	0.29	0.52	0.60	60	Y				1.65	0.6	1.30	31	Y	Y	
	1"	Zo-e-shield 6	WEA-N-289-00069-00001	0.31	0.21	0.47	59				Y	1.76	0.6	1.30	11			
	1"	Zo-e-shield 6 w/ Argon	WEA-N-289-00087-00001	0.28	0.21	0.47	63		Y	Y	Y	1.59	0.6	1.30	15			
	1"	Zo-e-shield 7 (Triple Glazed)	WEA-N-289-00183-00001	0.25	0.19	0.39	66	Y	Y	Y	Y	1.42	0.6	1.30	17	Y		
1"	Zo-e-shield 7 w/ Argon (Triple Glazed)	WEA-N-289-00185-00001	0.22	0.19	0.39	67	Y	Y	Y	Y	1.25	0.6	1.30	21	Y	Y		
Less Than 1" GIA or SDL	3/4"	Clear Insul	WEA-N-289-00040-00002	0.45	0.53	0.55	45					2.56	0.6	1.32	12			
	3/4"	Insul Low-E	WEA-N-289-00046-00002	0.31	0.29	0.48	56					1.76	0.6	1.32	16			
	3/4"	Insul Low E w/Argon	WEA-N-289-00052-00002	0.27	0.28	0.48	62	Y	Y			1.53	0.6	1.32	20	Y		
	3/4"	Bronze Low E	WEA-N-289-00048-00012	0.31	0.27	0.35	56					1.76	0.6	1.32	14			
	3/4"	Bronze Low E w/Argon	WEA-N-289-00055-00012	0.28	0.27	0.35	60		Y			1.59	0.6	1.32	18	Y		
	3/4"	Insul Low-E 340	WEA-N-289-00105-00002	0.31	0.13	0.26	57				Y	1.76	0.6	1.30	6			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-289-00120-00002	0.28	0.12	0.26	60		Y	Y	Y	1.59	0.6	1.30	10			
	3/4"	Zo-e-shield 5	WEA-N-289-00061-00002	0.31	0.19	0.43	57				Y	1.76	0.6	1.32	10			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-289-00079-00002	0.27	0.19	0.43	61	Y	Y	Y	Y	1.53	0.6	1.30	15			
	3/4"	Zo-e-shield 5 Extreme	WEA-N-289-00065-00002	0.26	0.19	0.42	44	Y	Y	Y	Y	1.48	0.6	1.32	16			
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-289-00083-00002	0.24	0.18	0.42	48	Y	Y	Y	Y	1.36	0.6	1.30	18	Y		
	3/4"	Insul Low-E 180	WEA-N-289-00095-00002	0.32	0.47	0.53	56					1.82	0.6	1.30	25			
	3/4"	Insul Low E 180 w/Argon	WEA-N-289-00110-00002	0.29	0.47	0.53	60	Y				1.65	0.6	1.30	28	Y		
	1"	Zo-e-shield 6	WEA-N-289-00069-00002	0.31	0.19	0.42	59				Y	1.76	0.6	1.30	10			
	1"	Zo-e-shield 6 w/ Argon	WEA-N-289-00087-00002	0.28	0.19	0.42	63		Y	Y	Y	1.59	0.6	1.30	14			
	1"	Zo-e-shield 7 (Triple Glazed)	WEA-N-289-00184-00001	0.26	0.17	0.34	66	Y	Y	Y	Y	1.48	0.6	1.30	15			
1"	Zo-e-shield 7 w/ Argon (Triple Glazed)	WEA-N-289-00186-00001	0.22	0.17	0.34	67	Y	Y	Y	Y	1.25	0.6	1.30	20	Y			
1" or Over GIA or SDL	3/4"	Clear Insul	WEA-N-289-00040-00003	0.45	0.47	0.49	45					2.56	0.6	1.32	8			
	3/4"	Insul Low-E	WEA-N-289-00046-00003	0.31	0.26	0.42	56					1.76	0.6	0.01	16			
	3/4"	Insul Low E w/Argon	WEA-N-289-00052-00003	0.27	0.25	0.42	62	Y	Y	Y	Y	1.53	0.6	1.32	18	Y		
	3/4"	Bronze Low E	WEA-N-289-00048-00013	0.31	0.24	0.31	56				Y	1.76	0.6	1.32	13			
	3/4"	Bronze Low E w/Argon	WEA-N-289-00055-00013	0.28	0.24	0.31	60		Y	Y	Y	1.59	0.6	1.32	16	Y		
	3/4"	Insul Low-E 340	WEA-N-289-00105-00003	0.31	0.12	0.23	57				Y	1.76	0.6	1.30	6			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-289-00120-00003	0.28	0.11	0.23	60		Y	Y	Y	1.59	0.6	1.30	9			
	3/4"	Zo-e-shield 5	WEA-N-289-00061-00003	0.31	0.17	0.38	57				Y	1.76	0.6	1.32	9			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-289-00079-00003	0.27	0.17	0.38	61	Y	Y	Y	Y	1.53	0.6	1.30	14			
	3/4"	Zo-e-shield 5 Extreme	WEA-N-289-00065-00003	0.26	0.17	0.37	44	Y	Y	Y	Y	1.48	0.6	1.32	15			
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-289-00083-00003	0.24	0.17	0.37	48	Y	Y	Y	Y	1.36	0.6	1.30	17	Y		
	3/4"	Insul Low-E 180	WEA-N-289-00095-00003	0.32	0.42	0.47	56					1.82	0.6	1.30	22			
	3/4"	Insul Low E 180 w/Argon	WEA-N-289-00110-00003	0.29	0.42	0.47	60	Y				1.65	0.6	1.30	26	Y		
	1"	Zo-e-shield 6	WEA-N-289-00069-00003	0.31	0.17	0.37	59				Y	1.76	0.6	1.30	9			
	1"	Zo-e-shield 6 w/ Argon	WEA-N-289-00087-00003	0.28	0.17	0.37	63		Y	Y	Y	1.59	0.6	1.30	12			
	1"	Zo-e-shield 7 (Triple Glazed)	WEA-N-289-00184-00002	0.26	0.16	0.30	66	Y	Y	Y	Y	1.48	0.6	1.30	14			
1"	Zo-e-shield 7 w/ Argon (Triple Glazed)	WEA-N-289-00186-00002	0.22	0.16	0.30	67	Y	Y	Y	Y	1.25	0.6	1.30	19	Y			

^a Total Unit calculations are derived from computer simulations that are then verified by 3rd party testing in accordance with NFRC 100-2004, NFRC 200-2004, and NFRC 500-2004.

^b Published values reflect 3mm/3mm glass lite thicknesses.

Revised 7/2/18

US Qualification Criteria	Climate Zone	U-Factor	*SHGC	
 As of January 2016	Northern	<=0.27	Any	Prescriptive
		=0.28	>=0.32	Equivalent Energy Performance
		=0.29	>=0.37	
		=0.30	>=0.42	
	North-Central	<=0.30	<=0.40	
	South-Central	<=0.30	<=0.25	
	Southern	<=0.40	<=0.25	

* SHGC = Solar Heat Gain Coefficient
Air Leakage <= 0.3 cfm/ft²