

# Thermal Performance Data

Visions 3500 Single Hung Picture/Transom Windows (9310)  
(non J-channel)



US Qualification Criteria	Climate Zone	U-Value	SHGC	
<p>As of January 2016</p>	Northern	$\leq 0.27$	Any	Prescriptive
		$\leq 0.28$	$\geq 0.32$	Equivalent Energy Performance
		$\leq 0.29$	$\geq 0.37$	
		$\leq 0.30$	$\geq 0.42$	
	North-Central	$\leq 0.30$	$\leq 0.40$	
	South-Central	$\leq 0.30$	$\leq 0.25$	
	Southern	$\leq 0.40$	$\leq 0.25$	

Canadian Qualification Criteria	Climate Zone	U-Value	or	Energy Rating
<p>As of February 2015</p>	Zone 1	$\leq 1.60$		$\geq 25$
	Zone 2	$\leq 1.40$		$\geq 29$
	Zone 3	$\leq 1.20$		$\geq 34$
	Air Leakage $\leq 0.3$ cfm/ft <sup>2</sup>			

## U-Value

A measurement of how much energy a material conducts. The lower the U-Value, the greater the insulating effect.

## Solar Heat Gain Coefficient (SHGC)

Measures how well a window or door prevents heat from passing through it. The lower a window or door's SHGC, the less heat it allows to pass through it.

## Visible Light Transmittance

The amount of light in the visible portion of the spectrum that passes through a glazing material.

## Condensation Resistance Rating

Measures how well a window resists the formation of condensation on the inside surface. The higher the number the better resistance to condensation.

## Energy Rating

A value demonstrating the balance between U-Value, SHGC and air leakage. The higher the number, the more efficient the product.

## R-Value

A measurement of how much a material resists heat transfer. A higher R-Value means a greater insulating effect and a lower rate of heat flow out of the home. While **R-value** measures resistance to heat transfer, **U-value** measures the rate of heat transfer. In simple terms, **U-value** is the mathematical reciprocal of **R-value**; that is, **U = 1/R and R = 1/U**.

<sup>a</sup> Total Unit calculations are derived from computer simulations that are then verified by 3rd party testing in accordance with NFRC 100, NFRC 200, and NFRC 500.

<sup>b</sup> Published values reflect 3mm/3mm glass lite thicknesses.

ENERGY PERFORMANCE DATA										CANADIAN ENERGY PERFORMANCE DATA									
Visions 3500 Single Hung Picture/Transom Windows (9310)										CANADA ENERGY STAR v 4.1									
Grille Option	Glazing thickness	aNFRC Total Unit Calculations bGlazing Option	CPD #	U-Value	Solar Heat Gain Coefficient	Visible Light Transmittance	Condensation Resistance Rating	US ENERGY STAR V 6.0				U-Value (metric)	Maximum Air Leakage L/s/m2	Air Infiltration/Exfiltration Average	Energy Rating	CANADA ENERGY STAR v 4.1			
								N	NC	SC	S					1	2	3	
No GIA or SDL	3/4"	Clear Insul	WEA-N-274-01191-00001	0.46	0.67	0.70	44					2.61	0.6	0.05	21				
	3/4"	Insul Low-E	WEA-N-274-01192-00001	0.31	0.36	0.61	56					1.76	0.6	0.05	22				
	3/4"	Insul Low E w/Argon	WEA-N-274-01200-00001	0.27	0.36	0.61	60	Y	Y			1.53	0.6	0.05	27	Y			
	3/4"	Passive Solar	WEA-N-274-01195-00001	0.31	0.59	0.68	56					1.76	0.6	0.05	35	Y	Y	Y	
	3/4"	Passive Solar w/Argon	WEA-N-274-01203-00001	0.28	0.59	0.68	59	Y				1.59	0.6	0.05	39	Y	Y	Y	
	3/4"	Zo-e-shield 5	WEA-N-274-01193-00001	0.30	0.24	0.55	57		Y	Y	Y		1.70	0.6	0.05	17			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-274-01201-00001	0.26	0.23	0.55	60	Y	Y	Y	Y		1.48	0.6	0.05	21	Y		
	3/4"	Zo-e-shield 5 Extreme	WEA-N-274-01194-00001	0.24	0.23	0.54	44	Y	Y	Y	Y		1.36	0.6	0.05	23	Y	Y	
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-274-01202-00001	0.22	0.23	0.54	48	Y	Y	Y	Y		1.25	0.6	0.05	26	Y	Y	
	1"	Zo-e-shield 6	WEA-N-274-01273-00001	0.30	0.24	0.55	58		Y	Y	Y		1.70	0.6	0.05	17			
	1"	Zo-e-shield 6 w/ Argon	WEA-N-274-01281-00001	0.26	0.23	0.55	61	Y	Y	Y	Y		1.48	0.6	0.05	21	Y		
	1"	Zo-e SafeGuard Certified	WEA-N-274-01278-00001	0.30	0.23	0.54	58		Y	Y	Y		1.70	0.6	0.05	16			
	1"	Zo-e SafeGuard Certified w/ Argon	WEA-N-274-01286-00001	0.26	0.23	0.54	62	Y	Y	Y	Y		1.48	0.6	0.05	21	Y		
	3/4"	Insul Low-E 240	WEA-N-274-01197-00001	0.31	0.22	0.34	56				Y		1.76	0.6	0.05	14			
	3/4"	Insul Low-E 240 w/Argon	WEA-N-274-01205-00001	0.27	0.22	0.34	59	Y	Y	Y	Y		1.53	0.6	0.05	19	Y		
	3/4"	Insul Low-E 340	WEA-N-274-01198-00001	0.30	0.16	0.33	56		Y	Y	Y		1.70	0.6	0.05	12			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-274-01206-00001	0.26	0.15	0.33	60	Y	Y	Y	Y		1.48	0.6	0.05	16	Y		
	3/4"	Bronze Low E	WEA-N-274-01192-00011	0.31	0.34	0.46	56						1.76	0.6	0.05	21			
3/4"	Bronze Low E w/Argon	WEA-N-274-01200-00011	0.27	0.34	0.46	60	Y	Y				1.53	0.6	0.05	26	Y			
Less Than 1" GIA or SDL	3/4"	Clear Insul	WEA-N-274-01191-00002	0.46	0.60	0.63	44					2.61	0.6	0.05	17				
	3/4"	Insul Low-E	WEA-N-274-01192-00002	0.31	0.32	0.55	56					1.76	0.6	0.05	20				
	3/4"	Insul Low E w/Argon	WEA-N-274-01200-00002	0.27	0.32	0.55	60	Y	Y			1.53	0.6	0.05	25	Y			
	3/4"	Passive Solar	WEA-N-274-01195-00002	0.31	0.53	0.61	56					1.76	0.6	0.05	32	Y	Y		
	3/4"	Passive Solar w/Argon	WEA-N-274-01203-00002	0.28	0.53	0.61	59	Y				1.59	0.6	0.05	36	Y	Y	Y	
	3/4"	Zo-e-shield 5	WEA-N-274-01193-00002	0.30	0.22	0.50	57		Y	Y	Y		1.70	0.6	0.05	15			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-274-01201-00002	0.26	0.21	0.50	60	Y	Y	Y	Y		1.48	0.6	0.05	20	Y		
	3/4"	Zo-e-shield 5 Extreme	WEA-N-274-01194-00002	0.24	0.21	0.48	44	Y	Y	Y	Y		1.36	0.6	0.05	22	Y	Y	
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-274-01202-00002	0.22	0.21	0.48	48	Y	Y	Y	Y		1.25	0.6	0.05	25	Y	Y	
	1"	Zo-e-shield 6	WEA-N-274-01273-00002	0.30	0.21	0.49	58		Y	Y	Y		1.70	0.6	0.05	15			
	1"	Zo-e-shield 6 w/ Argon	WEA-N-274-01281-00002	0.26	0.21	0.49	61	Y	Y	Y	Y		1.48	0.6	0.05	20	Y		
	1"	Zo-e SafeGuard Certified	WEA-N-274-01278-00002	0.30	0.21	0.48	58		Y	Y	Y		1.70	0.6	0.05	15			
	1"	Zo-e SafeGuard Certified w/ Argon	WEA-N-274-01286-00002	0.26	0.21	0.48	62	Y	Y	Y	Y		1.48	0.6	0.05	20	Y		
	3/4"	Insul Low-E 240	WEA-N-274-01197-00002	0.31	0.20	0.31	56				Y		1.76	0.6	0.05	13			
	3/4"	Insul Low-E 240 w/Argon	WEA-N-274-01205-00002	0.27	0.20	0.31	59	Y	Y	Y	Y		1.53	0.6	0.05	18	Y		
	3/4"	Insul Low-E 340	WEA-N-274-01198-00002	0.30	0.15	0.30	56		Y	Y	Y		1.70	0.6	0.05	11			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-274-01206-00002	0.26	0.14	0.30	60	Y	Y	Y	Y		1.48	0.6	0.05	16			
	3/4"	Bronze Low E	WEA-N-274-01192-00012	0.31	0.31	0.41	56						1.76	0.6	0.05	19			
3/4"	Bronze Low E w/Argon	WEA-N-274-01200-00012	0.27	0.31	0.41	60	Y	Y				1.53	0.6	0.05	24	Y			
1" Or Over GIA or SDL	3/4"	Clear Insul	WEA-N-274-01191-00003	0.46	0.54	0.56	44					2.61	0.6	0.05	14				
	3/4"	Insul Low-E	WEA-N-274-01192-00003	0.31	0.29	0.49	56					1.76	0.6	0.05	18				
	3/4"	Insul Low E w/Argon	WEA-N-274-01200-00003	0.27	0.29	0.49	60	Y	Y			1.53	0.6	0.05	23	Y			
	3/4"	Passive Solar	WEA-N-274-01195-00003	0.31	0.47	0.54	56					1.76	0.6	0.05	29	Y			
	3/4"	Passive Solar w/Argon	WEA-N-274-01203-00003	0.28	0.48	0.54	59	Y				1.59	0.6	0.05	33	Y	Y		
	3/4"	Zo-e-shield 5	WEA-N-274-01193-00003	0.30	0.20	0.44	57		Y	Y	Y		1.70	0.6	0.05	14			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-274-01201-00003	0.26	0.19	0.44	60	Y	Y	Y	Y		1.48	0.6	0.05	18	Y		
	3/4"	Zo-e-shield 5 Extreme	WEA-N-274-01194-00003	0.24	0.19	0.43	44	Y	Y	Y	Y		1.36	0.6	0.05	21	Y	Y	
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-274-01202-00003	0.22	0.19	0.43	48	Y	Y	Y	Y		1.25	0.6	0.05	24	Y	Y	
	1"	Zo-e-shield 6	WEA-N-274-01273-00003	0.30	0.19	0.44	58		Y	Y	Y		1.70	0.6	0.05	14			
	1"	Zo-e-shield 6 w/ Argon	WEA-N-274-01281-00003	0.26	0.19	0.44	61	Y	Y	Y	Y		1.48	0.6	0.05	18	Y		
	1"	Zo-e SafeGuard Certified	WEA-N-274-01278-00003	0.30	0.19	0.43	58		Y	Y	Y		1.70	0.6	0.05	14			
	1"	Zo-e SafeGuard Certified w/ Argon	WEA-N-274-01286-00003	0.26	0.19	0.43	62	Y	Y	Y	Y		1.48	0.6	0.05	18	Y		
	3/4"	Insul Low-E 240	WEA-N-274-01197-00003	0.31	0.18	0.27	56				Y		1.76	0.6	0.05	12			
	3/4"	Insul Low-E 240 w/Argon	WEA-N-274-01205-00003	0.27	0.18	0.27	59	Y	Y	Y	Y		1.53	0.6	0.05	17	Y		
	3/4"	Insul Low-E 340	WEA-N-274-01198-00003	0.30	0.13	0.26	56		Y	Y	Y		1.70	0.6	0.05	10			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-274-01206-00003	0.26	0.13	0.26	60	Y	Y	Y	Y		1.48	0.6	0.05	15			
	3/4"	Bronze Low E	WEA-N-274-01192-00013	0.31	0.28	0.37	56						1.76	0.6	0.05	18			
3/4"	Bronze Low E w/Argon	WEA-N-274-01200-00013	0.27	0.28	0.37	60	Y	Y				1.53	0.6	0.05	23	Y			