

Thermal Performance Data

Visions 3500 Slider Windows (9407)

(non J-channel)




ENERGY PERFORMANCE DATA														CANADIAN ENERGY PERFORMANCE DATA				
NFRC Total Unit Calculations ^a														ENERGY STAR				
Grille Option	Glazing thickness	Glazing Option ^b	CPD #	U Value	Solar Heat Gain Coefficient	Visible Light Transmittance	Condensation Resistance Rating	US ENERGY STAR V 6.0				U-Value (metric)	Maximum Air Leakage L/s/m ²	Air Infiltration/Exfiltration Average	Energy Rating	CANADA ENERGY STAR v 4.1		
								N	NC	SC	S					1	2	3
No GIA or SDL	3/4"	Clear Insul	WEA-N-275-00267-00001	0.46	0.62	0.65	48					2.61	0.6	0.56	18			
	3/4"	Insul Low-E	WEA-N-275-00273-00001	0.31	0.33	0.57	58					1.76	0.6	0.56	20			
	3/4"	Insul Low E w/Argon	WEA-N-275-00280-00001	0.27	0.33	0.57	63	Y	Y			1.53	0.6	0.56	25	Y		
	3/4"	Bronze Low E	WEA-N-275-00274-00011	0.32	0.32	0.42	57					1.82	0.6	0.56	18			
	3/4"	Bronze Low E w/Argon	WEA-N-275-00281-00011	0.28	0.32	0.42	57	Y	Y			1.59	0.6	0.56	23	Y		
	3/4"	Insul Low-E 340	WEA-N-275-00332-00001	0.31	0.15	0.31	58				Y	1.76	0.6	0.56	10			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-275-00347-00001	0.28	0.14	0.31	60		Y	Y	Y	1.59	0.6	0.56	13			
	3/4"	Zo-e-shield 5	WEA-N-275-00288-00001	0.31	0.22	0.51	57				Y	1.76	0.6	0.56	14			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-275-00306-00001	0.27	0.22	0.51	60	Y	Y	Y	Y	1.53	0.6	0.56	19	Y		
	3/4"	Zo-e-shield 5 Extreme	WEA-N-275-00292-00001	0.26	0.22	0.50	44	Y	Y	Y	Y	1.48	0.6	0.56	20	Y		
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-275-00310-00001	0.23	0.22	0.50	48	Y	Y	Y	Y	1.31	0.6	0.56	24	Y	Y	
	3/4"	Zo-e-shield 6	WEA-N-275-00293-00001	0.33	0.23	0.50	56				Y	1.87	0.6	0.56	12			
	3/4"	Zo-e-shield 6 w/ Argon	WEA-N-275-00311-00001	0.28	0.22	0.50	59		Y	Y	Y	1.59	0.6	0.56	18	Y		
	1"	Zo-e-shield 7 (Triple Glazed)	WEA-N-275-00480-00001	0.25	0.20	0.41	61	Y	Y	Y	Y	1.42	0.6	0.56	20	Y		
	1"	Zo-e-shield 7 w/ Argon (Triple Glazed)	WEA-N-275-00482-00001	0.21	0.20	0.41	64	Y	Y	Y	Y	1.19	0.6	0.56	25	Y	Y	Y
Less Than 1" GIA or SDL	3/4"	Clear Insul	WEA-N-275-00267-00004	0.46	0.56	0.58	48					2.61	0.6	0.56	15			
	3/4"	Insul Low-E	WEA-N-275-00273-00004	0.31	0.30	0.51	58					1.76	0.6	0.56	18			
	3/4"	Insul Low E w/Argon	WEA-N-275-00280-00004	0.27	0.30	0.51	63	Y	Y			1.53	0.6	0.56	24	Y		
	3/4"	Bronze Low E	WEA-N-275-00274-00014	0.32	0.29	0.38	57					1.82	0.6	0.56	17			
	3/4"	Bronze Low E w/Argon	WEA-N-275-00281-00014	0.28	0.28	0.38	57		Y			1.59	0.6	0.56	21	Y		
	3/4"	Insul Low-E 340	WEA-N-275-00332-00004	0.31	0.14	0.28	58				Y	1.76	0.6	0.56	9			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-275-00347-00004	0.28	0.13	0.28	60		Y	Y	Y	1.59	0.6	0.56	12			
	3/4"	Zo-e-shield 5	WEA-N-275-00288-00004	0.31	0.20	0.46	57				Y	1.76	0.6	0.56	13			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-275-00306-00004	0.27	0.20	0.46	60	Y	Y	Y	Y	1.53	0.6	0.56	18	Y		
	3/4"	Zo-e-shield 5 Extreme	WEA-N-275-00292-00004	0.26	0.20	0.45	44	Y	Y	Y	Y	1.48	0.6	0.56	19	Y		
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-275-00310-00004	0.23	0.20	0.45	48	Y	Y	Y	Y	1.31	0.6	0.56	23	Y	Y	
	3/4"	Zo-e-shield 6	WEA-N-275-00294-00003	0.35	0.20	0.45	51				Y	1.99	0.6	0.56	8			
	3/4"	Zo-e-shield 6 w/ Argon	WEA-N-275-00312-00003	0.30	0.20	0.45	59		Y	Y	Y	1.70	0.6	0.56	14			
	1"	Zo-e-shield 7 (Triple Glazed)	WEA-N-275-00481-00003	0.27	0.18	0.37	61	Y	Y	Y	Y	1.53	0.6	0.56	17	Y		
	1"	Zo-e-shield 7 w/ Argon (Triple Glazed)	WEA-N-275-00483-00003	0.23	0.18	0.37	64	Y	Y	Y	Y	1.31	0.6	0.56	21	Y	Y	
1" or Over GIA or SDL	3/4"	Clear Insul	WEA-N-275-00267-00005	0.46	0.50	0.52	48					2.61	0.6	0.56	11			
	3/4"	Insul Low-E	WEA-N-275-00273-00005	0.31	0.27	0.45	58					1.76	0.6	0.56	17			
	3/4"	Insul Low E w/Argon	WEA-N-275-00280-00005	0.27	0.27	0.45	63	Y	Y			1.53	0.6	0.56	22	Y		
	3/4"	Bronze Low E	WEA-N-275-00274-00015	0.32	0.26	0.33	57					1.82	0.6	0.56	15			
	3/4"	Bronze Low E w/Argon	WEA-N-275-00281-00015	0.28	0.26	0.33	57		Y			1.59	0.6	0.56	20	Y		
	3/4"	Insul Low-E 340	WEA-N-275-00332-00005	0.31	0.12	0.24	58				Y	1.76	0.6	0.56	8			
	3/4"	Insul Low-E 340 w/Argon	WEA-N-275-00347-00005	0.28	0.12	0.24	60		Y	Y	Y	1.59	0.6	0.56	12			
	3/4"	Zo-e-shield 5	WEA-N-275-00288-00005	0.31	0.18	0.41	57				Y	1.76	0.6	0.56	12			
	3/4"	Zo-e-shield 5 w/ Argon	WEA-N-275-00306-00005	0.27	0.18	0.41	60	Y	Y	Y	Y	1.53	0.6	0.56	17	Y		
	3/4"	Zo-e-shield 5 Extreme	WEA-N-275-00292-00005	0.26	0.18	0.40	44	Y	Y	Y	Y	1.48	0.6	0.56	18	Y		
	3/4"	Zo-e-shield 5 Extreme w/ Argon	WEA-N-275-00310-00005	0.23	0.18	0.40	48	Y	Y	Y	Y	1.31	0.6	0.56	21	Y	Y	
	3/4"	Zo-e-shield 6	WEA-N-275-00294-00004	0.35	0.18	0.40	51				Y	1.99	0.6	0.56	7			
	3/4"	Zo-e-shield 6 w/ Argon	WEA-N-275-00312-00004	0.30	0.18	0.40	59		Y	Y	Y	1.70	0.6	0.56	13			
	1"	Zo-e-shield 7 (Triple Glazed)	WEA-N-275-00481-00004	0.27	0.17	0.32	61	Y	Y	Y	Y	1.53	0.6	0.56	16	Y		
	1"	Zo-e-shield 7 w/ Argon (Triple Glazed)	WEA-N-275-00483-00004	0.23	0.17	0.32	64	Y	Y	Y	Y	1.31	0.6	0.56	21	Y	Y	

^a Total Unit calculations are derived from computer simulations that are then verified by 3rd party testing in accordance with NFRC 100-2004, NFRC 200-2004, and NFRC 500-2004.

Revised 6/15/17

^b Published values reflect 3mm/3mm glass lite thicknesses.

US Qualification Criteria	Climate Zone	U-Factor	*SHGC	
 As of January 2016	Northern	<=0.27	Any	Prescriptive
		=0.28	>=0.32	Equivalent Energy Performance
		=0.29	>=0.37	
		=0.30	>=0.42	
	North-Central	<=0.30	<=0.40	
	South-Central	<=0.30	<=0.25	
Southern	<=0.40	<=0.25		

* SHGC = Solar Heat Gain Coefficient
 Air Leakage <= 0.3 cfm/ft²